

Birch Ply

KingSize



Metsä Wood KingSize is an extra large size birch plywood panel jointed from standard size panels. KingSize panels enable larger one piece components. The largest available panel size is 13700 mm x 2800 mm.

APPLICATIONS

Metsä Wood KingSize is suitable for applications that require large size panels and high technical properties. Larger panels facilitate and accelerate installation and provide structures with a high degree of rigidity.

- Transport industry: Trailer, truck, lorry, van and refrigerated trailer floors, container floors, walls and ceilings, passenger car floors, railway wagon floors and ship/boat decking
- Building applications: Concrete formwork, loading docks, piers, stages and sport stands

MAJOR ADVANTAGES

- Extra large sizes
- Strong and rigid
- Withstands impacts and other forms of bruising
- Available with durable and weather resistant overlays
- Dimensionally stable
- Easy to machine and fasten using conventional woodworking tools and fasteners
- Environmentally friendly
- Weather and boil proof bonding

BASE PLYWOOD

The base plywood of Metsä Wood KingSize is Metsä Wood Birch, which is made of cross-bonded 1.4 mm thick birch veneers and bonded with weather and boil-resistant phenol formaldehyde adhesive.

KingSize panels are scarf-jointed from standard size birch plywood panels using weather resistant melamine or resorcinol adhesive. The scarf-joints appear as thin, visible lines on both sides of the panel, running perpendicularly to the panel length.

OVERLAY

Metsä Wood KingSize panels can be either wood faced or overlaid with phenolic films.

The main King Size panel options are:

- Metsä Wood Birch KingSize (BB/WG)
- Metsä Wood Form KingSize (smooth surface)
- Metsä Wood Deck KingSize (wire mesh surface)

In the overlaid panels, the reverse side is overlaid with smooth phenolic film.

SURFACE PROPERTIES

Metsä Wood KingSize panels have the same surface properties as the original panels, possibly with slight differences in colouration and gloss between the jointed panels. The surface quality of the wood faced KingSize panels is BB/WG. The scarf-joint may cause a slight variation in the thickness.

Surface properties are dependent on the overlay type. More information on the overlay selection and the surface properties of a single overlay type, contact Metsä Wood Plywood sales or see particular Product Data Sheet (Metsä Wood Birch, Form or Deck).

EDGE SEALING

Panel edges of the overlaid panels are sealed against moisture absorption with acrylic edge sealing paint. The colour of the edge sealing is normally dark brown. Even though edge sealing slows down the absorption of moisture into the panel, it does not eliminate it completely.

PANEL SIZES

Maximum size of Metsä Wood KingSize is 13700 mm x 2800 mm.
The first measurement indicates the orientation of the surface veneer grain.

SIZE TOLERANCES

Measured in accordance with standard EN 324, the plywood size and squareness tolerances meet EN 315 requirements.

PANEL TOLERANCES

LENGTH / WIDTH	TOLERANCE
< 1000 mm	±1 mm
1000-2000 mm	±2 mm
> 2000 mm	±3 mm
Squareness	±0.1 % or ±1 mm/m
Edge straightness	±0.1 % or ±1 mm/m

THICKNESS, STRUCTURES AND THICKNESS TOLERANCES

THICKNESSES, STRUCTURES AND THICKNESS TOLERANCES OF THE PANELS *

NOMINAL THICKNESS (mm)	NUMBER OF PLYS (pcs)	THICKNESS TOLERANCE		WEIGHT kg/m ²
		min. (mm)	max. (mm)	
9	7	8.6	9.5	6.1
12	9	11.3	12.5	8.2
15	11	14.1	15.3	10.2
18	13	16.9	18.1	12.2
21	15	19.8	20.9	14.3
24	17	22.7	23.7	16.3
27	19	25.0	26.8	18.4
30	21	27.9	29.9	20.4

* Moisture content of the product affects its dimensions

* Average density of Metsä Wood birch plywood is 680 kg /m³ (at relative humidity of RH 65%)

* Special structures and thicknesses are available on request

* Customised tolerances are possible but must be agreed separately

METSÄ WOOD

P.O. Box 50, 02020 Metsä, Finland
Tel. +358 1046 05

www.metsawood.com/plywood

BONDING CLASSES

Metsä Wood plywood panels are bonded with a weather and boil-resistant phenol formaldehyde adhesive (WBP, BFU, AW, exterior).

The gluing meets the requirements of the following international standards:

- EN 314-2 / Class 3 (exterior)
- DIN 68705-3 / BFU 100
- BS 6566 Part 8 / WBP

The scarf joint is glued with weather resistant melamine or resorcinol adhesive.

FORMALDEHYDE EMISSIONS

Formaldehyde emissions are dependent on the overlay type.

More information on the formaldehyde emissions of a single overlay type, see particular Product Data Sheet (Metsä Wood Birch, Form or Deck).

PANEL STRENGTH PROPERTIES

Due to the scarf jointed core plywood, the strength values of Metsä Wood KingSize in the longitudinal direction of the panel are ca. 65% of standard Metsä Wood Birch plywood values. In the cross direction of the panel the strength values are similar to standard Birch plywood. Stiffness values in both directions are similar to standard Birch plywood.

MECHANICAL PROPERTIES OF METSÄ WOOD KINGSIZE PANELS.

MOISTURE CONTENT 12%. THE VALUES ARE EN 789 VALUES.

THICKNESS (mm)	MEAN MODULUS OF ELASTICITY (N/mm ²)		CHARACTERISTIC BENDING STRENGTH (N/mm ²)	
		⊥		⊥
9	11395	6105	29.6	32.1
12	10719	6781	27.9	33.2
15	10316	7184	26.8	33.8
18	10048	7452	26.1	34.1
21	9858	7642	25.6	34.3
24	9717	7783	25.3	34.4
27	9607	7893	25.0	34.5
30	9519	7981	24.8	34.6

The Concrete formwork design data (permissible concrete pressure tables, design nomograms) for all Metsä Wood formwork panels can be found in Metsä Wood Concrete Formwork technical data.

MACHINING

Metsä Wood KingSize plywood panels can be machined according to customer specification on special request.

PACKING

Metsä Wood KingSize panels are packed either in covered pallets or moisture resistant plastic wrapping. The packing quantities must be agreed case by case.

FURTHER INFORMATION

- Metsä Wood Transport brochure
- Metsä Wood Concrete Formwork brochure
- Metsä Wood Concrete Formwork technical data

This leaflet is provided for information purposes only and no liability or responsibility of any kind is accepted by Metsä Wood or their representatives, although Metsä Wood has used reasonable efforts to verify the accuracy of any advice, recommendation or information. Metsä Wood reserves the right to alteration of its products, product information and product range without any notice.

