

# Spruce Ply



Metsä Wood Spruce is an uncoated softwood plywood manufactured from a long-grained, homogenous Nordic conifer with straight fibres. It is an excellent general-purpose construction panel, ideal for both interior and exterior construction work and any other uses where strength, stability, light weight and versatility are valued.

## APPLICATIONS

Metsä Wood Spruce is a multi-purpose construction panel that is also suitable for various other applications.

- **Building applications:** floor, wall and roof structures, renovations, agricultural structures, pedestrian bridges, construction platforms etc.
- **Concrete formwork:** concrete moulds for arched casting and other loose-panel formwork
- **Transport industry:** walls of containers, coaches and trailers etc.
- **Other applications:** packing applications, furniture, fences, hoardings, canopies etc.

## MAJOR ADVANTAGES

- Lightweight and dimensionally stable
- Strong and rigid
- Can act simultaneously as load-bearing construction and stiffening element
- Easy to machine and install using conventional woodworking tools and fasteners
  - panel is impact resistant and does not crumble
  - good base for fasteners
- Environmentally friendly
- Available with square edges and tongue-and-groove profiles
- Weather- and boil-proof bonding

## BASE PLYWOOD

Metsä Wood Spruce plywood is made of cross-bonded 3 mm thick coniferous veneers and bonded with a weather- and boil-resistant phenol formaldehyde adhesive.

## SURFACE PROPERTIES

Metsä Wood Spruce plywood panels can be unsanded or sanded on both sides. The surface can be treated with standard paints, lacquers, varnishes and protection treatments applicable to wood products. It is recommended to confirm the compatibility of the surface treatment with the supplier.

The surface grades are determined by the grade of the surface veneers as follows:

| Spruce plywood surfaces | Typical properties  |
|-------------------------|---|
| II                      | – sound surface, might be repaired with filler, unrepaired defects with Ø max. 5 mm are permitted |
| III+                    | – open defects repaired with filler   |
| III                     | – standard quality, with open defects such as knotholes and veneer checks                         |

Primary grade combinations are II/III and III/III.

Classification of Metsä Wood Spruce surface grade meets the requirements of EN 635.

## PANEL SIZES

Metsä Wood Spruce is available in sizes:

- 2400 / 2440 / 2500 mm x 1200 / 1220 / 1250 mm
- 2400 / 2440 mm x 600 / 610 mm

The first measurement indicates the orientation of the surface veneer grain.

Other sizes are available on request.

## SIZE TOLERANCES

Measured in accordance with standard EN 324, the plywood size and squareness tolerances meet the requirements of EN 315.

### PANEL TOLERANCES

| LENGTH / WIDTH    | TOLERANCE         |
|-------------------|-------------------|
| < 1000 mm         | ±1 mm             |
| 1000-2000 mm      | ±2 mm             |
| > 2000 mm         | ±3 mm             |
| Squareness        | ±0.1 % or ±1 mm/m |
| Edge straightness | ±0.1 % or ±1 mm/m |

## THICKNESS, STRUCTURES AND THICKNESS TOLERANCES

The thickness tolerances fulfil the requirements of standard EN 315 and are, in part, more stringent than the official requirements.

### THICKNESSES, STRUCTURES AND THICKNESS TOLERANCES OF THE PANELS\*

| NOMINAL THICKNESS (mm) | NUMBER OF PLYS (no.) | THICKNESS TOLERANCE |           | WEIGHT kg/m <sup>2</sup> |
|------------------------|----------------------|---------------------|-----------|--------------------------|
|                        |                      | min. (mm)           | max. (mm) |                          |
| 9                      | 3                    | 8.8                 | 9.5       | 4.1                      |
| 12                     | 4                    | 11.5                | 12.5      | 5.5                      |
| 15                     | 5                    | 14.3                | 15.3      | 6.9                      |
| 18                     | 6                    | 17.1                | 18.1      | 8.3                      |
| 21                     | 7                    | 20.0                | 20.9      | 9.7                      |
| 24                     | 8                    | 22.9                | 23.7      | 11.0                     |
| 27                     | 9                    | 25.2                | 26.8      | 12.4                     |
| 30                     | 10                   | 28.1                | 29.9      | 13.8                     |

\* The moisture content of the product affects its dimensions

\* Average density of Metsä Wood Spruce plywood is 460 kg/m<sup>3</sup> (at a relative humidity of 65%)

\* Special structures and thicknesses are available on request

\* Customised tolerances are possible but must be agreed separately

## METSÄ WOOD

P.O. Box 50, 02020 Metsä, Finland

Tel. +358 1046 05

[WWW.METSAWOOD.COM/PLYWOOD](http://WWW.METSAWOOD.COM/PLYWOOD) →

## BONDING CLASSES

Metsä Wood plywood panels are bonded with a weather- and boil-resistant phenol formaldehyde adhesive (WBP, BFU, AW, exterior).

The gluing meets the requirements of the following international standards:

- EN 314-2 / Class 3 (exterior)
- DIN 68705-3 / BFU 100
- BS 6566 Part 8 / WBP
- JAS / Structural plywood / Class 2

## FORMALDEHYDE EMISSIONS

Determined according to EN 717-1, the formaldehyde emitted by Metsä Wood Spruce falls far below the Class E1 requirement of ≤ 0.100 ppm and also fulfils the most stringent requirements in the world (≤ 0.030 ppm). The formaldehyde emission of Metsä Wood Spruce is approximately 0.018 ppm.

## PANEL STRENGTH PROPERTIES

Metsä Wood Spruce is a CE marked product. The strength and elasticity properties are specified according to standards EN 789 and EN 1058 and can be found in the Metsä Wood Spruce Declaration of Performance (DoP). The DoP documents can be downloaded from [www.metsawood.com/dop](http://www.metsawood.com/dop).

## MACHINING

Metsä Wood Spruce plywood can be delivered with tongue-and-groove edge machining on either two sides or four sides. Tongue-and-groove panels are always sanded. Tongue-and-groove machining decreases net panel size by 10 mm. Tongue-and-groove machining is available for panel thicknesses ≥ 12 mm.

## PACKING

Metsä Wood Spruce panels are packed in moisture resistant plastic wrapping.

### PACKING QUANTITIES

| PANEL SIZE                      | mm | NUMBER OF PANELS PER PALLET BY THICKNESS |     |     |     |    |    |    |    |
|---------------------------------|----|--|-----|-----|-----|----|----|----|----|
|                                 |    | 9  | 12  | 15  | 18  | 21 | 24 | 27 | 30 |
| 2400/2440/2500 x 1200/1220/1250 |    | 110                                      | 85  | 65  | 55  | 45 | 40 | 35 | 30 |
| 2400/2440 x 600/610             |    | 220                                      | 170 | 130 | 110 | 90 | 80 | 70 | 60 |

## FURTHER INFORMATION

- Metsä Wood Spruce Declaration of Performance ([www.metsawood.com/dop](http://www.metsawood.com/dop))
- Metsä Wood Spruce Plywood Manual
- Metsä Wood Spruce Plywood for Construction brochure
- Metsä Wood Concrete Formwork brochure

This leaflet is provided for information purposes only and no liability or responsibility of any kind is accepted by Metsä Wood or their representatives, although Metsä Wood has used reasonable efforts to verify the accuracy of any advice, recommendation or information. Metsä Wood reserves the right to make alterations to its products, product information and product range without prior notice.

